



## TECHNICAL FOLDER

## POLITEX V70C

### Specifications

<b>Code</b>	SF70CV
<b>Name</b>	V70C
<b>Description</b>	GLASS FIBER FILTER MEDIA

### Applications

Coalescent pre-filter in turbo-gas plants. Pre-filtration in civil and industrial air treatment plants.

### Sizes

dimensions	roll 0,635x20	m
------------	---------------	---

### Technical data

composition	glass fiber	
regeneration	no	
nominal thickness	60	mm
max. working temperature	120	°C
max. working R.H.	100	%
nominal weight	280	g/m <sup>2</sup>
advisable cross speed	1,5 - 2,5	m/s
initial pressure drop	28 - 48	Pa
final pressure drop	250	Pa
average gravimetric efficiency	89	%
dust holding capacity	422	g/m <sup>2</sup>
classification (EN 779:2012)	G3	
classification (ISO 16890)	coarse 50	%
flame resistance	F1 - DIN.53438	

Rev. 01\_12

#### GENERAL FILTER HEADQUARTER

Via Emilia, 23  
31038 Paese (TV), Italia  
Tel: +39 0422 4594  
Fax: +39 0422 459590  
www.generalfilter.com  
info@generalfilter.com

#### GENERAL FILTER ITALIA

Via Morgagni, 40 int. 7/8  
20010 Pogliano Milanese (MI), Italia  
Tel: +39 02 93550640  
Fax: +39 02 93255670  
Italia: sales.ita@generalfilter.com  
Estero: sales.int@generalfilter.com

#### GENERAL FILTER FRANCE

13 Avenue d'Aygu  
26200 Montelimar, France  
Tel: +33 987876598  
Fax: +33 987876599  
r.meucci@generalfilter.fr

#### GENERAL FILTER IBERICA

Calle Salamanca 21  
28500 Arganda del Rey, Madrid,  
España  
Tel: +34 91 8719046  
Fax: +34 91 8719054  
gefisa@generalfilter.com

#### GENERAL FILTER HAVAK

Sanayi Sitesi P. Blok No. 10  
Hosdere Mevkii  
34517 Esenyurt, Istanbul, Türkiye  
Tel: +90 212 623 0074  
Fax: +90 212 623 0075  
info@generalfilterhavak.com